

INCRETE SINGLE COMPONENT FINE SPRAY-DECK GROUT

POLYMER-MODIFIED CEMENTITIOUS COATING



EUCLID CHEMICAL

PACKAGING

50 lb (22.7 kg) bag

YIELD

150 ft² (13.9 m²) for a skim coat, 75 ft² (6.96 m²) for a final coat.

MINIMUM/MAXIMUM APPLICATION THICKNESS

Min: 1/16 inch

Max: 1/4 inch

APPEARANCE

Dry white powder

CLEAN UP

Clean tools and equipment with water before the material hardens.

SHELF LIFE

1 year in original, unopened package

SPECIFICATIONS AND COMPLIANCES

VOC Content: <5 g/L

BRIEF OVERVIEW

INCRETE SINGLE-COMPONENT FINE SPRAY-DECK GROUT is a pre-blended cementitious coating, and is an ideal horizontal or vertical cover-up for unsightly existing concrete and masonry. INCRETE SINGLE-COMPONENT FINE SPRAY-DECK GROUT produces a smooth-finish surface. This product may be sprayed or troweled down and accepts most Increte branded stains. May be integrally colored as well with INCRETE COLOR PACKS.

PRODUCT CHARACTERISTICS

ADVANTAGES

- Single Component
- Easy to mix and use
- Durable, wear-resistant
- May be integrally colored
- Interior or exterior use
- May be stained

COMMON USES

- Masks concrete repairs
- Fill in and repairs spalls
- Fresh canvas for stain application
- Beautify pool decks, walkways, etc.
- Residential & commercial areas
- Patios
- Plazas
- Showroom floors
- Vertical applications

COMMON APPLICATION METHODS

- Trowelable (horizontal applications)
- Squeegee
- Sprayable

PHYSICAL PROPERTIES

- 4-6 quarts of water per 50 lb bag
- Working Time/Drying Time: 20-30 minutes
- Allow to dry 24 hours before sealing

DIRECTIONS FOR USE

For complete detailed instructions, consult INCRETE SPRAY-DECK/TEXTURE-CRETE Installation Instructions.

SURFACE PREPARATION

Concrete surfaces must be structurally sound, free of loose or deteriorated concrete and free of dust, dirt, paint, efflorescence, oil and all other contaminants. Remove any loose material and any coatings such as paint, curing agents, and sealers. INCRETE UNI-STRIPP is perfect for removing old coatings. Clean surface with a cleaner/degreaser specifically designed for concrete and paver surfaces. Mechanically abrade the surface to achieve a surface profile equal to CSP 2-3 in accordance with ICRI Guideline 310.2. Properly clean profiled area.

MIXING

Add 4 to 6 qt (3.8 to 5.4 L) of clean, potable, cold water to a clean 5 gal (18.9 L) pail plastic pail. Begin mixing while slowly adding one 50 lb (22.7 kg) bag of INCRETE SINGLE-COMPONENT FINE SPRAY-DECK GROUT. Continue mixing for 2 to 3 minutes.

APPLICATION

The grout can then be troweled, squeegeed, or sprayed on the surface at a thickness not to exceed 1/4 in (6.35 mm).

SEAL

After at least 24 hours drying time, the surface must be scraped, broomed, and blown with a high velocity blower and then sealed with INCRETE CLEAR SEAL or INCRETE CONCRETE STAIN SEALER. INCRETE SHUR-GRIP may be added to the sealer for additional slip resistance.

MAINTENANCE

Sweep surface as necessary. Wash surface with a mild soap/detergent and rinse with water. Clean surface with a cleaner/degreaser specifically designed for concrete and paver surfaces.

PRECAUTIONS/LIMITATIONS

- Avoid applying material in direct sun.
- Use only potable water for mixing.
- DO NOT use this material below 50°F (10°C).
- When using in warm conditions, follow the recommendations in ACI 305R "Guide to Hot Weather Concreting".
- Store product in a cool, dry place.
- In all cases, consult the Safety Data Sheet before use

Rev. 07.21

WARRANTY: The Euclid Chemical Company ("Euclid") solely and expressly warrants that its products shall be free from defects in materials and workmanship for one (1) year from the date of purchase. Unless authorized in writing by an officer of Euclid, no other representations or statements made by Euclid or its representatives, in writing or orally, shall alter this warranty. EUCLID MAKES NO WARRANTIES, IMPLIED OR OTHERWISE, AS TO THE MERCHANTABILITY OR FITNESS FOR ORDINARY OR PARTICULAR PURPOSES OF ITS PRODUCTS AND EXCLUDES THE SAME. If any Euclid product fails to conform with this warranty, Euclid will replace the product at no cost to Buyer. Replacement of any product shall be the sole and exclusive remedy available and buyer shall have no claim for incidental or consequential damages. Any warranty claim must be made within one (1) year from the date of the claimed breach. Euclid does not authorize anyone on its behalf to make any written or oral statements which in any way alter Euclid's installation information or instructions in its product literature or on its packaging labels. Any installation of Euclid products which fails to conform with such installation information or instructions shall void this warranty. Product demonstrations, if any, are done for illustrative purposes only and do not constitute a warranty or warranty alteration of any kind. Buyer shall be solely responsible for determining the suitability of Euclid's products for the Buyer's intended purposes.