



DURAL 106

PRECAST SEGMENTAL EPOXY ADHESIVE

PACKAGING

3 gal (11.4 L) unit
 Code: TD63333 (Class D)
 Code: TD63133 (Class E)
 Code: TD63233 (Class F)

CLEAN UP

Clean tools and application equipment immediately with acetone, xylene, or MEK. Clean spills or drips with the same solvents while still wet. Hardened DURAL 106 will require mechanical abrasion for removal.

SHELF LIFE

2 years in original, unopened package

SPECIFICATIONS AND COMPLIANCES

- Complies with ASTM C881 Type VI, Grade 3, Classes D, E, and F

DESCRIPTION

DURAL 106 is a two-component, moisture insensitive, 100% solids epoxy adhesive for use as a bonding agent for precast segmental box girders, bridge and other segmental construction. DURAL 106 is a non-sag paste which provides a 6 hour contact time before joining.

PRODUCT CHARACTERISTICS

Class	Temperature Application Range
D	40 °F to 65 °F (4 °C to 18 °C)
E	60 °F to 90 °F (16 °C to 32 °C)
F	85 °F to 115 °F (29 °C to 46 °C)

APPEARANCE

Part A liquid is white in color and Part B liquid is black in color.

COVERAGE

Covers approximately 12 ft²/gal to 13 ft²/gal (0.29 m²/L to 0.32 m²/L) at 1/8 inch (3 mm) thickness.

Note: Coverage rates are approximate. Actual coverage depends on temperature, texture, and substrate porosity.

TECHNICAL INFORMATION

The following are typical values obtained under laboratory conditions. Expect reasonable variation under field conditions.

Test Method	Property	Class D	Class E	Class F
-	Temperature Range	40 °F to 65 °F (4 °C to 18 °C)	60 °F to 90 °F (16 °C to 32 °C)	85 °F to 115 °F (29 °C to 46 °C)
-	Sag Resistance at High Temperature	< 1/4 in (6.4 mm)	< 1/4 in (6.4 mm)	< 1/4 in (6.4 mm)
-	Gel Time at High Temperature	4 hours	3 hours 40 minutes	5 hours
ASTM D695	Compressive Yield	7 days: 11,390 psi (78.5 MPa) 14 days: 12,350 psi (85.1 MPa)	7 days: 6,023 psi (41.5 MPa) 14 days: 8,510 psi (58.7 MPa)	7 days: 3,220 psi (22.2 MPa) 14 days: 6,150 psi (42.4 MPa)
ASTM D648	Heat Deflection Temperature, Minimum	> 140 °F (60 °C)	> 140 °F (60 °C)	154 °F (67 °C)
-	Open Contact Time at High Temperature	6 hours	6 hours	6 hours
ASTM C882	Bond Strength	14 days: > 3,710 psi (25.6 MPa)	14 days: > 5,065 psi (34.9 MPa)	14 days: > 3,810 psi (26.3 MPa)
ASTM C882	Contact Strength	2 days: 1,100 psi (7.6 MPa)	14 days: 3,623 psi (24.9 MPa)	14 days: 1,380 psi (9.5 MPa)

DIRECTIONS FOR USE

Surface Preparation: The surface must be dry and structurally sound. The substrate must also be free of all dust, dirt, grease, oil, coatings, laitance and other contaminants that would interfere with proper adhesion. The surface should be lightly sand blasted, shot blasted or water blasted with a minimum pressure of 5,000 psi (34.5 MPa). Wet surfaces must be dried. Remove all visible water with a heater and/or oil-free air compressor. Any dust that may have accumulated between cleaning and application of DURAL 106 should be removed by an oil-free air compressor.

Mixing: Do not begin mixing until the segment is prepared for installation. Mix DURAL 106 using a low-speed drill and a mixing paddle. Pre-mix Part A and Part B separately for approximately 1 minute each. Combine all of Part A with all of Part B, then mix thoroughly for 3 to 5 minutes. Scrape the bottom and sides of the containers at least once during mixing. Do not scrape bottom or sides of the container once mixing operations have ceased; doing so may result in unmixed resin or hardener being applied to the substrate. Unmixed resin or hardener will not cure properly. Do not aerate the material during mixing. To keep aeration to a minimum, the recommended mixing paddles are #P1 or #P2 as found in ICRI Guideline 320.5R-2014.

Application: Use a trowel, brush, mop or gloved hand to apply DURAL 106 on both segments to be joined. Apply at minimum and uniform thickness of 1/16 inch (1.6 mm). A visible bead line must be observed on all exposed contact areas. DURAL 106 should be applied completely around the pre-stressing ducts but not within 3/8 inch (9.5 mm) of the ducts. Use DURAL 106 Class D, E or F depending on the temperature range prevailing at the time of installation. DURAL 106 should be applied within the first half of its gel time. Erection, assembly and temporary post tensioning must be completed within the contact time of DURAL 106. The segments should be joined with a minimum provisional stress of 30 psi (0.21 MPa) across the entire cross section. If the segments have not been joined within 70% of the contact (open) time, the operation should be discontinued, the DURAL 106 removed and fresh DURAL 106 applied. After the segments have been joined, excess DURAL 106 should be removed from the joints, where accessible. Tendon ducts should be swabbed immediately after stressing to remove or smooth out any epoxy in the conduit and to seal any pockets or air bubble holes that may have formed at the joint.

PRECAUTIONS/LIMITATIONS

- Store DURAL 106 indoors, protected from moisture, at temperatures between 50 °F and 90 °F (10 °C and 32 °C).
- Surface and ambient temperature during applications should be between 40 °F and 115 °F (4 °C and 46 °C). This range covers all three classes of DURAL 106 epoxy, and the proper class must be chosen based on the prevailing temperature at the time of installation.
- Material temperatures should be at least 40 °F (4 °C) and rising.
- Working time and cure time will decrease as the temperature increases, and will increase as the temperature decreases.
- Do not thin DURAL 106.
- DURAL 106 will discolor upon prolonged exposure to ultraviolet light and high-intensity artificial lighting.
- Apply DURAL 106 to dry concrete surfaces only.
- DURAL 106 is not intended for use in areas that are subject to prolonged and/or strong chemical attack.
- Do not apply to frozen or frost-filled substrates, or when the temperature is below 40 °F (4 °C) or expected to fall below that temperature within 24 hours of application.
- In all cases, consult the product Safety Data Sheet before use.

Rev. 10.23

WARRANTY: The Euclid Chemical Company ("Euclid") solely and expressly warrants that its products shall be free from defects in materials and workmanship for one (1) year from the date of purchase. Unless authorized in writing by an officer of Euclid, no other representations or statements made by Euclid or its representatives, in writing or orally, shall alter this warranty. EUCLID MAKES NO WARRANTIES, IMPLIED OR OTHERWISE, AS TO THE MERCHANTABILITY OR FITNESS FOR ORDINARY OR PARTICULAR PURPOSES OF ITS PRODUCTS AND EXCLUDES THE SAME. If any Euclid product fails to conform with this warranty, Euclid will replace the product at no cost to Buyer. Replacement of any product shall be the sole and exclusive remedy available and buyer shall have no claim for incidental or consequential damages. Any warranty claim must be made within one (1) year from the date of the claimed breach. Euclid does not authorize anyone on its behalf to make any written or oral statements which in any way alter Euclid's installation information or instructions in its product literature or on its packaging labels. Any installation of Euclid products which fails to conform with such installation information or instructions shall void this warranty. Product demonstrations, if any, are done for illustrative purposes only and do not constitute a warranty or warranty alteration of any kind. Buyer shall be solely responsible for determining the suitability of Euclid's products for the Buyer's intended purposes.