



DURAL AQUA-DAM LV

LOW VISCOSITY, HYDROPHOBIC POLYURETHANE GROUT

EUCLID CHEMICAL

PACKAGING

5 gal (19 L) pail
Code: 043B 00

55 gal (208 L) drum
Code: 043B 55

Dural Aquaccelerator:

1 pint (0.47 L) cans
Code: 043AA 00

5 gal (19 L) pail
Code: 043AA 05

Dural Pump Rinse:

5 gal (19 L) pail
Code: 043F 05

CLEAN UP

Use all appropriate protective equipment. Avoid contact with the active grout. Use DURAL PUMP RINSE to clean out the lines of the injection equipment. DURAL PUMP RINSE can then be left in the lines as a primer, prior to the next project. Be sure to expel all DURAL PUMP RINSE from the lines prior to the next grouting job, for it will drastically affect the curing capability of the grout.

SHELF LIFE

1 year in original, unopened containers

DESCRIPTION

DURAL AQUA-DAM LV is a low viscosity, hydrophobic polyurethane compound that is injected into hairline cracks in concrete and other sound substrates to stop water from entering into occupied or unwanted places. The reaction time of the DURAL AQUA-DAM LV is controlled through the use of its accelerator, known as DURAL AQUACCELERATOR. DURAL AQUA-DAM LV forms a water tight seal within the substrate that remains even if the water subsides.

PRODUCT CHARACTERISTICS

FEATURES/BENEFITS

- Low viscosity for smaller cracks
- Bonds to wet and dry substrates
- Needs very little water to react and cure
- Remains active when the water subsides
- Excellent elongation to handle moving cracks and joints
- Fast reaction time with added accelerator

PRIMARY APPLICATIONS

- Sealing fine cracks & joints
- Below grade walls subject to high water tables
- Sewers & manholes
- Mines & tunnels
- Can be used in porous soils as a stabilizer

TECHNICAL INFORMATION

The following are typical values obtained under laboratory conditions. Expect reasonable variation under field conditions.

Test Method	Typical Properties - Liquid	Results
ASTM D1638	Viscosity @ 77 °F (25 °C)	100 cps
-	Specific Gravity	1.17
-	Physical State	Liquid
-	Color	Amber

Test Method	Typical Properties - Cured	Results
ASTM D1622	Density	4 lb/ft ³ (64 kg/m ³)
ASTM D638	Elongation	48%
ASTM D638	Tensile Strength	25 psi (0.17 MPa)
ASTM C273	Shear Strength	19 psi (0.13 MPa)
ASTM D2842	Water Absorption	< 1% by volume

Typical Reaction Profile			
AQUACCELERATOR PERCENTAGE	0%	1.25%	2.5%
Initial Foam	Not Recommended	45 sec	30 sec
Reaction Time	Not Recommended	3 min	1 min 45 sec

WARRANTY: The Euclid Chemical Company ("Euclid") solely and expressly warrants that its products shall be free from defects in materials and workmanship for one (1) year from the date of purchase. Unless authorized in writing by an officer of Euclid, no other representations or statements made by Euclid or its representatives, in writing or orally, shall alter this warranty. EUCLID MAKES NO WARRANTIES, IMPLIED OR OTHERWISE, AS TO THE MERCHANTABILITY OR FITNESS FOR ORDINARY OR PARTICULAR PURPOSES OF ITS PRODUCTS AND EXCLUDES THE SAME. If any Euclid product fails to conform with this warranty, Euclid will replace the product at no cost to Buyer. Replacement of any product shall be the sole and exclusive remedy available and buyer shall have no claim for incidental or consequential damages. Any warranty claim must be made within one (1) year from the date of the claimed breach. Euclid does not authorize anyone on its behalf to make any written or oral statements which in any way alter Euclid's installation information or instructions in its product literature or on its packaging labels. Any installation of Euclid products which fails to conform with such installation information or instructions shall void this warranty. Product demonstrations, if any, are done for illustrative purposes only and do not constitute a warranty or warranty alteration of any kind. Buyer shall be solely responsible for determining the suitability of Euclid's products for the Buyer's intended purposes.

DIRECTIONS FOR USE

Surface & Crack Preparation: To ensure the crack or joint is treated properly, clean the exterior of the concrete surface so that the full extent of the crack or joint can be seen. This will aid in properly locating the injection holes to be drilled. To properly locate holes, start by determining the thickness of the concrete section that is to be injected. Layout alternating hole locations on either side of the crack/joint running full length of the crack/joint. Space the holes running parallel to the crack at a distance equal to the thickness of the concrete being injected. Place the holes at a proper distance from the crack or joint so that a hole drilled at a 45 degree angle will intersect the crack at the mid-point of the concrete thickness. Adjust the hole layout as necessary to assure that drilling operations do not come into contact with existing reinforcing steel or other embedded items. Drill 5/8" (16mm) holes at 45 degrees to intersect the crack/joint at the mid-point of the concrete thickness. Ensure that the drill bit is long enough to intersect the crack. Clear drilled holes of all dust, debris and laitance. Install 5/8" (16mm) injection packers into the holes and tighten. Inject water through the packers. Ensure that water injected into the packers is flowing through the holes and crack/joint and ensure that the packers are not leaking.

In cases where drilling holes at an angle will result in chipping or breaking of the concrete, the holes may need to be drilled directly into the face of the crack/joint. In such cases the distance between the holes should be equal to the concrete thickness and the hole depth should be one half of the concrete thickness.

Mixing: Prior to injecting DURAL AQUA-DAM LV, properly stir the material and the accelerator. Do not use high speed mixing equipment, for that will "whip" air into the product. Pour the appropriate amount of DURAL AQUACCELERATOR into the DURAL AQUA-DAM LV and mix on slow speed for a minute or two, to ensure the accelerator is fully mixed in. The mixing ratios are as follows:

DURAL AQUA-DAM LV	DURAL AQUACCELERATOR		
	Standard Amount	Minimum	Maximum
Package Size			
5 gal (19 L) Pail	16 oz. (0.47 L)	8 oz. (0.24 L)	32 oz. (0.94 L)
55 gal (208 L) Drum	1.25 gal (4.75 L)	80 oz. (2.4 L)	2.5 gal (9.5 L)

The standard mixing ratio should be used in most instances. Do not go below the minimum mixing amount, for the material will struggle to react, especially in colder weather. Do not add more than the maximum amount of accelerator for the material will face a great risk of shrinking, thus allowing water to pass through the crack or joint again.

Placement: Once the injection packers have been set and the drilled holes and crack have been flushed out with water, the injection of the material can begin. Start at the lowest point of a vertical crack and work upwards. Pump DURAL AQUA-DAM LV into the packer until foaming material comes out the face of the crack and starts to approach the next packer. On a horizontal crack, start at the end that was first installed and flushed with water. The more water left in the crack and injection site, the better. Move the injection head to the second packer and repeat until you have moved the entire length of the crack. A standard airless paint pump can be used for this application. Typical injection pressure into cracks is 200 to 3,000 psi (1.4 to 20 MPa), depending on the width and depth of the crack. Once the DURAL AQUA-DAM LV has cured, the packers can be removed or cut off, flush with the surrounding surface. The grout that has cured outside of the face of the crack can be cut back with a margin trowel or similar scraping tool. The packer holes can then be filled in with Euclid Chemical's Speed Plug hydraulic cement and finished as desired.

PRECAUTIONS/LIMITATIONS

- Colder temperatures will affect the viscosity and setting times of the product.
- Avoid exceeding 90 °F (32 °C) when warming product.
- Water used to react DURAL AQUA-DAM LV must be in the pH range of 3 to 10.
- Store material in moisture free packaging. Atmospheric moisture may cause a foam "head" inside of pail. This can be peeled off and the material below can still be usable.
- In all cases, consult the Safety Data Sheet before use.

Rev. 10.23

WARRANTY: The Euclid Chemical Company ("Euclid") solely and expressly warrants that its products shall be free from defects in materials and workmanship for one (1) year from the date of purchase. Unless authorized in writing by an officer of Euclid, no other representations or statements made by Euclid or its representatives, in writing or orally, shall alter this warranty. EUCLID MAKES NO WARRANTIES, IMPLIED OR OTHERWISE, AS TO THE MERCHANTABILITY OR FITNESS FOR ORDINARY OR PARTICULAR PURPOSES OF ITS PRODUCTS AND EXCLUDES THE SAME. If any Euclid product fails to conform with this warranty, Euclid will replace the product at no cost to Buyer. Replacement of any product shall be the sole and exclusive remedy available and buyer shall have no claim for incidental or consequential damages. Any warranty claim must be made within one (1) year from the date of the claimed breach. Euclid does not authorize anyone on its behalf to make any written or oral statements which in any way alter Euclid's installation information or instructions in its product literature or on its packaging labels. Any installation of Euclid products which fails to conform with such installation information or instructions shall void this warranty. Product demonstrations, if any, are done for illustrative purposes only and do not constitute a warranty or warranty alteration of any kind. Buyer shall be solely responsible for determining the suitability of Euclid's products for the Buyer's intended purposes.