



DURALTEX FAST

RAPID TURNAROUND EPOXY FLOOR COATING

PACKAGING

Clear & Standard Colors

15 gal (56.8 L) unit

Code: TD4309203\$MCK

3 gal (11.4 L) pail

Code: TD4309215\$M

CLEAN UP

Clean tools and application equipment immediately with acetone, xylene, or MEK. Clean spills or drips with the same solvents while still wet. Hardened DURALTEX FAST will require mechanical abrasion for removal.

SHELF LIFE

2 years in original, properly stored, unopened package

DESCRIPTION

DURALTEX FAST is a versatile, fast-setting, 100% solids, two-component epoxy for flooring applications. Ideally suited for rapid turnaround projects.

PRODUCT CHARACTERISTICS

FEATURES/BENEFITS

- Fast-curing - for rapid turnaround in busy areas
- Versatile – neat coatings, broadcast floors, chipfloors, slurry, broadcast and trowel down
- Chemically resistant
- Low modulus
- Low odor – 100% solids

PRIMARY APPLICATIONS

- Entryways and storage areas
- Production rooms and loading docks
- Warehouse and garage floors
- Manufacturing plants, workshops
- Educational facilities and hospitals
- Kitchens, lavatories and showers

APPEARANCE

DURALTEX FAST is available in White, Light Reflective, Clear, Tan, Light Gray, Concrete Gray, Medium Gray, Dark Gray, Black, and Tile Red.

COVERAGE

Neat Coating 20 – 30 mils thick	Coverage- ft ² /gal (m ² /L)	Trowel Down Coating 1/8" - 1/4" thick	Coverage - ft ² /gal (m ² /L)
Duraltex Fast (clear): prime coat	200 to 225 (4.9 to 5.5)	Duraltex Fast (clear): prime coat	200 to 225 (4.9 to 5.5)
Duraltex Fast: 1 st coat	100 (2.5)	Trowel coat 1/8" (3.2 mm) thick (mortar):	
Duraltex Fast: 2 nd coat	150 (3.7)	40 lbs (18 kg) silica sand 20/40 mesh & 1 gal (3.8 L) Duraltex Fast	40 to 45 (0.98 to 1.1)
Aggregate Broadcast Coating, 1/16" - 1/8" thick		Seal coat: (select one- minimum)	
Duraltex Fast (clear): 1 st coat	100 (2.5)	Duraltex Fast	100 to 150 (2.5 to 3.7)
Broadcast aggregate to refusal	0.5 to 1.0 lbs/ft ² (2.4 to 4.9 kg/m ²)	Eucothane	200 to 250 (4.9 to 6.1)
Seal coat: (select one- minimum)			
Duraltex Fast	100 to 150 (2.5 to 3.7)		
Eucothane	200 to 250 (4.9 to 6.1)		

Note: Coverage rates are approximate. Actual coverage depends on temperature, texture, and substrate porosity.

TECHNICAL INFORMATION

The following are typical values obtained under laboratory conditions. Expect reasonable variation under field conditions.

*Material properties @ 75°F (24°C)

Test Method	Test Property	Values
ASTM C1583	Bond Strength	Greater than concrete
ASTM D695	Compressive Strength	Neat resin, 7 days. 11,500 psi (79.3 MPa)
N/A	Gel Time	200 g 15 to 20 minutes
ASTM D2240	Hardness, Shore D	80 to 90
N/A	Mix Ratio (by volume)	2:1
N/A	Pot Life, 3 gal (11.4 L)	15 to 30 minutes
N/A	Tack Free	3 to 4 hours
ASTM D638	Tensile Strength	5,500 psi to 6,500 psi (37.9 MPa to 44.8 MPa)
ASTM D638	Tensile Elongation	5 to 15 %
N/A	Viscosity: Part A	2,700 cp
N/A	Viscosity: Part B	200 cp
N/A	Viscosity: Mixed	930 cp
N/A	VOC Content	< 50 g/L
ASTM D570	Water Absorption, 24 hours	<0.5%

WARRANTY: The Euclid Chemical Company ("Euclid") solely and expressly warrants that its products shall be free from defects in materials and workmanship for one (1) year from the date of purchase. Unless authorized in writing by an officer of Euclid, no other representations or statements made by Euclid or its representatives, in writing or orally, shall alter this warranty. EUCLID MAKES NO WARRANTIES, IMPLIED OR OTHERWISE, AS TO THE MERCHANTABILITY OR FITNESS FOR ORDINARY OR PARTICULAR PURPOSES OF ITS PRODUCTS AND EXCLUDES THE SAME. If any Euclid product fails to conform with this warranty, Euclid will replace the product at no cost to Buyer. Replacement of any product shall be the sole and exclusive remedy available and buyer shall have no claim for incidental or consequential damages. Any warranty claim must be made within one (1) year from the date of the claimed breach. Euclid does not authorize anyone on its behalf to make any written or oral statements which in any way alter Euclid's installation information or instructions in its product literature or on its packaging labels. Any installation of Euclid products which fails to conform with such installation information or instructions shall void this warranty. Product demonstrations, if any, are done for illustrative purposes only and do not constitute a warranty or warranty alteration of any kind. Buyer shall be solely responsible for determining the suitability of Euclid's products for the Buyer's intended purposes.

DIRECTIONS FOR USE

Surface Preparation: The surface must be structurally sound, clean and free of grease, oil, curing compounds, soil, dust and other contaminants. See note in "Precautions/Limitations" section if coating is to be placed over old/existing epoxy or urethane coatings. New concrete and masonry must be at least 28 days old. Surface laitance must be removed. Concrete surfaces must be roughened and made absorptive, preferably by mechanical means, and then thoroughly cleaned of all dust and debris. If the surface was prepared by chemical means (acid etching), a water/baking soda or water/ammonia mixture, followed by a clean water rinse, must be used for cleaning, in order to neutralize the substrate. The Concrete Surface Profile (CSP) should be equal to CSP 2-3 in accordance with Guideline 310.2R-2013, published by the International Concrete Repair Institute (ICRI). Allow substrate to dry before coating application. Following surface preparation, the strength of the surface can be tested if quantitative results are required by project specifications. An elcometer or similar tensile pull tester may be used in accordance with ASTM C1583, and the tensile pull-off strength should be at least 250 psi (1.7 MPa).

Do not apply epoxy or urethane coatings if there is excessive moisture in the concrete, or if the moisture vapor emission rate (MVER) is high. Before application of DURALTEX FAST, perform either of these tests: **ASTM F2170** - Standard Test Method for Determining Relative Humidity in Concrete Floor Slabs Using In-Situ Probes, or **ASTM F1869** - Standard Test Method for Measuring Moisture Vapor Emission Rate of Concrete Subfloor Using Anhydrous Calcium Chloride. If the relative humidity is 85% or greater, or the MVER is 3 lbs/1000 ft²/24 hrs or greater, use a moisture mitigation system such as Dural Aquatight 100 PLUS or Dural Aquatight WB. After surface preparation and moisture testing, a test section application is recommended to confirm good adhesion and compatibility of the coating with the surface, and to confirm appearance and aesthetics.

When coating steel, all contamination should be removed and the steel surface prepared to a "near white" finish (SSPC SP10) using clean, dry blasting media.

Mixing: Mix DURALTEX FAST using a low-speed drill and a mixing paddle. Pre-mix Part A and Part B separately for approximately 1 minute each. Combine Part A and Part B in a 2:1 ratio by volume, then mix thoroughly for 3 to 5 minutes. Scrape the bottom and sides of the containers at least once during mixing. Do not scrape bottom or sides of the container once mixing operations have ceased; doing so may result in unmixed resin or hardener being applied to the substrate. Unmixed resin or hardener will not cure properly. Do not aerate the material during mixing. To keep aeration to a minimum, the recommended mixing paddles are #P1 or #P2 as found in ICRI Guideline 320.5R-2014.

Application: See the "Epoxy & Urethane Coatings Application Guide" for installation means and methods. Note that any coverage rates or mixing ratios for epoxy or epoxy-aggregate combinations found in the "Epoxy & Urethane Coatings Application Guide" are approximations, and are for general reference only. For product-specific coverage rates and mixing ratios, refer to this technical data sheet.

PRECAUTIONS/LIMITATIONS

- Store DURALTEX FAST indoors, protected from moisture, at temperatures between 50 °F and 90 °F (10 °C and 32 °C)
- Surface and ambient temperature during coating applications should be between 50 °F and 90 °F (10 °C and 32 °C)
- Material temperatures should be at least 50 °F (10 °C) and rising
- Do not apply DURALTEX FAST if surface temperature is within 5 °F (3 °C) of the dew point in the work area
- Working time and cure time will decrease as the temperature increases, and will increase as the temperature decreases
- Do not thin DURALTEX FAST
- When a vapor barrier is utilized in on-grade applications of DURALTEX FAST, it must be installed directly under the slab
- Although DURALTEX FAST is chemically resistant, surface staining of the coating may occur after contact with some chemicals. Consider the use of a urethane topcoat such as EUCOTHANE for improved stain resistance.
- DURALTEX FAST will discolor upon prolonged exposure to ultraviolet light and high-intensity artificial lighting. An aliphatic urethane topcoat such as EUCOTHANE can minimize these effects.
- Depending on the condition of the substrate, minor surface defects can appear in the coating when applied. Proper surface prep, patching of substrate imperfections, and priming will ensure a better overall finish.
- If coating over old/existing epoxy or urethane coatings, or if more than 24 hours elapses between coats: sand the previous coat, wipe clean, and proceed with coating operations. If old/existing coatings are peeling, flaking, etc., all unsound material must be removed prior to new coating applications.
- Application of a test area is recommended to confirm final appearance and texture of the system with the end user
- In all cases, consult the product Safety Data Sheet before use

Rev. 11.23

WARRANTY: The Euclid Chemical Company ("Euclid") solely and expressly warrants that its products shall be free from defects in materials and workmanship for one (1) year from the date of purchase. Unless authorized in writing by an officer of Euclid, no other representations or statements made by Euclid or its representatives, in writing or orally, shall alter this warranty. EUCLID MAKES NO WARRANTIES, IMPLIED OR OTHERWISE, AS TO THE MERCHANTABILITY OR FITNESS FOR ORDINARY OR PARTICULAR PURPOSES OF ITS PRODUCTS AND EXCLUDES THE SAME. If any Euclid product fails to conform with this warranty, Euclid will replace the product at no cost to Buyer. Replacement of any product shall be the sole and exclusive remedy available and buyer shall have no claim for incidental or consequential damages. Any warranty claim must be made within one (1) year from the date of the claimed breach. Euclid does not authorize anyone on its behalf to make any written or oral statements which in any way alter Euclid's installation information or instructions in its product literature or on its packaging labels. Any installation of Euclid products which fails to conform with such installation information or instructions shall void this warranty. Product demonstrations, if any, are done for illustrative purposes only and do not constitute a warranty or warranty alteration of any kind. Buyer shall be solely responsible for determining the suitability of Euclid's products for the Buyer's intended purposes.