Master Format #: 00 00 00

EUCEM™ AEM 8



AIR ENTRAINING AND WORKABILITY AGENT FOR MASONRY CEMENTS

PRODUCT INFORMATION

PACKAGING

Available in 55 gal (208 L) drums, 264 gal (1000 L) totes, and bulk

SHELF LIFE

12 months

TECHNICAL INFORMATION

Active ingredients:

Aqueous solution of organic components

Freezing Point: < -15°C

Flash Point: >100°C

DESCRIPTION

EUCEM AEM 8 is a grinding aid specifically formulated to entrain air into masonry type cements and improved the water retention characteristics.

PRODUCT CHARACTERISTICS

FEATURES & BENEFITS

- Strong tension-active action.
- Better control of air contents, optimised bubble size and spacing. Good air retention properties.
- Easier and more thorough mortar mixing.
- Improved trowelability.
- Improved flowability.
- Improved water tightness.
- Reduces plastic shrinkage (initial set).
- Improved physical properties of the ground material.
- Improved performance in both closed and open circuit systems at equal specific surface area or equal sieve residues.
- Powder flow characteristics are improved before, during and after storage.

APPLICATIONS

• Masonry type cements N, S and M.

TECNICAL INFORMATION

% Solids	Specific Gravity @ 77°F (25 °C)	pH per Electrode
(ASTM C494)	(ASTM D1298)	@ 77°F (25 °C)
26.0 - 28.0	1.030 - 1.050	10.0 - 12.0

DIRECTIONS FOR USE

DOSAGE

The dosage range is typically between 0.08 and 0.2% per cement weight. Optimum dosage should be determined by plant trials and subsequent mortar evaluations.

PROCEDURE

Liquid admixture ready-to-use. A dosing pump is required to introduce the correct dosage into the mill. EUCEM AEM 8 may be introduced directly into the mill or onto the feed conveyor belt.

Our technicians are ready to provide advice and assistance in the use of EUCEM AEM 8.

PRECAUTIONS/LIMITATIONS

- The quality is guaranteed for 12 months starting from the manufacturing date provided the product is not altered with other chemicals.
- · Do not mix with any other product.
- Refer to Safety Data Sheet for additional information.

Rev. 05.22