



VERTICOAT SUPREME

SINGLE COMPONENT, VERTICAL & OVERHEAD REPAIR MORTAR WITH CORROSION INHIBITOR

PACKAGING

50 lb (22.7 kg) bag
Code: 160V 50

APPROXIMATE YIELD

50 lb (22.7 kg) unit: 0.48 ft³ (0.014 m³)
per unit when mixed with 2.75 quarts
(2.6 L) of potable water.

MINIMUM/MAXIMUM APPLICATION THICKNESS

1/4 to 2 inches (6 mm to 51 mm)

CLEAN UP

Clean tools and equipment with water before the material hardens.

SHELF LIFE

2 years in original, unopened package

SPECIFICATIONS AND COMPLIANCES

- Canadian Food Inspection Agency, MTO

DESCRIPTION

VERTICOAT SUPREME is a single component, microsilica and latex modified, non-sag concrete repair mortar designed for trowel applied vertical and overhead repairs requiring structural strength and high performance.

PRODUCT CHARACTERISTICS

FEATURES/BENEFITS

- One component for easy mixing and handling
- Excellent freeze-thaw resistance for difficult climates
- Microsilica and latex modified
- Contains an integral corrosion inhibitor
- Low permeability helps protect rebar from corrosion
- High bond strength provides excellent adhesion

PRIMARY APPLICATIONS

- Vertical and overhead repairs
- Marine structures, tunnels and dams
- Parking structures & bridges
- Parapet walls
- Above and below grade applications

APPEARANCE

VERTICOAT SUPREME is a free-flowing powder designed to be mixed with water. After mixing and placing, the color may initially appear darker than the surrounding concrete. While this color will lighten up substantially as the VERTICOAT SUPREME cures and dries out, the repair may always appear somewhat darker than the surrounding concrete.

TECHNICAL INFORMATION

The following are typical values obtained under laboratory conditions. Expect reasonable variation under field conditions.

Test Method	Test Property	Values
	Working Time	Approximately 30 minutes
ASTM C266	Set Time	Initial Set 1 hour Final Set 3 hours
	Unit Weight	approximately 115 lb/ft ³ (1,842 kg/m ³)
ASTM C109M 2" (50 mm) cubes	Compressive Strength	1 day 2,000 psi (13.8 MPa) 7 days 3,500 psi (24.1 MPa) 28 days 5,500 psi (37.9 MPa)
ASTM C348	Flexural Strength	7 days 900 psi (6.2 MPa) 28 days 1,000 psi (6.9 MPa)
ASTM C157*	Linear Shrinkage	3 days - 0.03% 7 days - 0.06% 14 days - 0.08% 28 days - 0.10% 56 days - 0.11%
ASTM C666 Procedure A	Freeze/Thaw Resistance	300 cycles . . . 90% relative dynamic modulus

*Based on initial length @ 24 hours; 50% RH @ 23 °C (73 °F)

WARRANTY: The Euclid Chemical Company ("Euclid") solely and expressly warrants that its products shall be free from defects in materials and workmanship for one (1) year from the date of purchase. Unless authorized in writing by an officer of Euclid, no other representations or statements made by Euclid or its representatives, in writing or orally, shall alter this warranty. EUCLID MAKES NO WARRANTIES, IMPLIED OR OTHERWISE, AS TO THE MERCHANTABILITY OR FITNESS FOR ORDINARY OR PARTICULAR PURPOSES OF ITS PRODUCTS AND EXCLUDES THE SAME. If any Euclid product fails to conform with this warranty, Euclid will replace the product at no cost to Buyer. Replacement of any product shall be the sole and exclusive remedy available and buyer shall have no claim for incidental or consequential damages. Any warranty claim must be made within one (1) year from the date of the claimed breach. Euclid does not authorize anyone on its behalf to make any written or oral statements which in any way alter Euclid's installation information or instructions in its product literature or on its packaging labels. Any installation of Euclid products which fails to conform with such installation information or instructions shall void this warranty. Product demonstrations, if any, are done for illustrative purposes only and do not constitute a warranty or warranty alteration of any kind. Buyer shall be solely responsible for determining the suitability of Euclid's products for the Buyer's intended purposes.

DIRECTIONS FOR USE

Surface Preparation: Concrete surfaces must be structurally sound, free of loose or deteriorated concrete and free of dust, dirt, paint, efflorescence, oil and all other contaminants. Mechanically abrade the surface to achieve a surface profile equal to CSP 6 - 8 in accordance with ICRI Guideline 310.2. Properly clean profiled area.

Priming & Bonding (Saw Cut & Chipped Out Repairs): Thoroughly clean any exposed reinforcing steel, and apply DURALPREP A.C. to the concrete and the reinforcing steel within the repair area. Refer to the DURALPREP A.C. technical data sheet for full instructions. Alternatively, application of EUCOWELD 2.0 to a dry substrate or a scrub coat of VERTICOAT SUPREME to the saturated surface dry (SSD) concrete surface may be used for bonding. The repair material must be placed on the scrub coat before the scrub coat dries out.

Priming & Bonding (Vertical & Overhead Skim Coats): Apply EUCOWELD 2.0 to a dry substrate or a scrub coat of VERTICOAT SUPREME to the saturated surface dry (SSD) concrete surface. The repair material must be placed on the scrub coat before the scrub coat dries out.

Mixing: Single bags may be mixed with a drill and "jiffy" type mixer. Use a paddle type mortar mixer for large jobs. All materials should be in the proper temperature range of 60 to 90 °F (16 to 32 °C). Add the appropriate amount of water for the batch size 2.5 to 3.0 qt (2.4 to 2.8 L) per bag, then add the dry product. Mix for 3 to 5 minutes. Do not mix more material than can be placed within 20 minutes.

Placement: Place in 1/4" to 2" (6 to 51 mm) lifts. Trowel into place and allow to stiffen before the next lift. If additional lifts are required after material has hardened, score the surface before proceeding to the next lift.

Finishing: Finish the repair material to the desired texture. Do not add additional water to the surface during the finishing operation. Use EU COBAR evaporation retarder.

Curing and Sealing: Curing is required. Cure with a Euclid Chemical high solids, water-based curing compound. (NOTE: A SOLVENT BASED CURING COMPOUND SHOULD NOT BE USED ON THIS PRODUCT). Under hot, windy or direct sunlight situations, apply a second coat of curing compound after the first has dried. If a curing compound is not desired, wet cure for a minimum of three days.

PRECAUTIONS/LIMITATIONS

- Do not allow repairs to freeze until the material has reached a minimum of 1,000 psi (7 MPa) compressive strength.
- Use only potable water for mixing.
- Minimum application thickness 1/4" (6 mm).
- Minimum surface and ambient temperature 45 °F (7 °C) and rising at time of application.
- When necessary, follow the recommendations in ACI 305R "Guide to Hot Weather Concreting" or ACI 306R "Guide to Cold Weather Concreting".
- For optimum results, condition material to 65 to 85 °F (18 to 29 °C) at least 24 hours prior to use.
- Do not use a solvent based curing compound on this product.
- In all cases, consult the Safety Data Sheet before use.

Rev. 11.23

WARRANTY: The Euclid Chemical Company ("Euclid") solely and expressly warrants that its products shall be free from defects in materials and workmanship for one (1) year from the date of purchase. Unless authorized in writing by an officer of Euclid, no other representations or statements made by Euclid or its representatives, in writing or orally, shall alter this warranty. EUCLID MAKES NO WARRANTIES, IMPLIED OR OTHERWISE, AS TO THE MERCHANTABILITY OR FITNESS FOR ORDINARY OR PARTICULAR PURPOSES OF ITS PRODUCTS AND EXCLUDES THE SAME. If any Euclid product fails to conform with this warranty, Euclid will replace the product at no cost to Buyer. Replacement of any product shall be the sole and exclusive remedy available and buyer shall have no claim for incidental or consequential damages. Any warranty claim must be made within one (1) year from the date of the claimed breach. Euclid does not authorize anyone on its behalf to make any written or oral statements which in any way alter Euclid's installation information or instructions in its product literature or on its packaging labels. Any installation of Euclid products which fails to conform with such installation information or instructions shall void this warranty. Product demonstrations, if any, are done for illustrative purposes only and do not constitute a warranty or warranty alteration of any kind. Buyer shall be solely responsible for determining the suitability of Euclid's products for the Buyer's intended purposes.